

CHEMICAL COMPOSITION (%)

Steel Group	C	Si	Mn	P max	S max	V
St35, E235, OLT35	max 0.17	max 0.35	min 0.40	0.025	0.025	
St45, OLT45	max 0.21	max 0.35	min 0.40	0.025	0.025	
St52, E355, OL52.3k	max 0.22	max 0.55	max 1.60	0.025	0.025	
E410, STE460	0.16÷0.22	0.10÷0.50	1.30÷1.70	0.030	0.035	0.08÷0.15