

## Mechanical Properties

<b>Steel group</b>	<b>Tensile Strength</b>	<b>Yield Strength min.</b>	<b>Elongation min.</b>	<b>Min. impact energy</b>	
	<b>MPa</b>	<b>MPa</b>	<b>%</b>	<b>J</b>	<b>°C</b>
P215NL	360÷480	215	25	40	-40
P265NL	410÷570	265	24	40	-40
Grade 6	min. 415	240	30	18	-45